

COATED FABRIC HP1032

HP1032 is a general purpose

silicone rubber-coated fiberglass fabric featuring abrasion resistance, excellent electrical properties and an operating temperature range of -85°F to +500°F. Typical applications include electrical gasketing, heater covering, conveyor belts, shrink tunnel curtains, release or separator fabrics.

Typical Physical Properties*

Property	Units	Value
Weight	Oz./Yd.2 Avg.	32
Overall Thickness	Inches	0.032
Fiberglass Thickness	Inches	0.015
Tensile Strength (Warp)	Lbs./In.	400
Tensile Strength (Fill)	Lbs./In.	300
Tear Strength (Warp)	Gr.	12,000
Tear Strength (Fill)	Gr.	12,000
Elongation	%	<10
Burst, Diaphragm	psi	200
Thread Count (Warp)		28
Thread Count (Fill)		16
Temperature Range		-85°F - +500°F
Color		White

*Values are typical properties and should not be used for writing specifications.

Availability

HP1032 is sold by the yard in continuous lengths, 36" wide.

HP1032 is a standard non-stock item. Please contact customer service for minimum order quantities, price and delivery.

Hi-Performance Products, INC.
1231 Puerta Del Sol, Unit 400
San Clemente CA 92673
Customer Service: (949)366-6088

ptfeglass.com

Limited Warranty: For a period of 6 months from the date of first sale, Hi-Performance Products warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). Hi-Performance Products **DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

NOTE: Hi-Performance Products does not assume any responsibility or liability for any, advice furnished, by it, or for the performance, or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and / or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.