

COATED FABRIC HP1410

HP1410 is a silicone rubber dispersion-coated nylon fabric, developed to meet the requirements of Boeing Materials Specification BMS-1-17D, type I and II, Grade B. HP1410 is suitable for continuous exposure to weather. It is not recommended for use with hydrocarbon fuels, oils or lubricants.

Typical Physical Properties*

Property	Units	Value
Weight	Oz./Yd.2 Avg.	7
Overall Thickness	Inches	0.009
Burst Strength	Lbs./Min.	400
Tear Strength (As received)	Lbs./Min.	80
Tear Strength (After abrasion)	Lbs./Min.	35
Air Permeability	CFM/Sq. Ft., Max	2.0
Stiffness (Type I)	mm, Max	250
Stiffness (Type II)	mm, Max	100
Color		White

*Values are typical properties and should not be used for writing specifications.

Availability

HP1410 is sold by the yard in continuous lengths, 36" wide.

HP1410 is a custom product. Please contact customer service for minimum order quantities, price and delivery.

Application Advantages

- Resistant to creasing and corrosion.
- Resistant to wear and tear.

Hi-Performance Products, INC.
1231 Puerta Del Sol, Unit 400
San Clemente CA 92673
Customer Service: (949)366-6088

ptfeglass.com

Limited Warranty: For a period of 6 months from the date of first sale, Hi-Performance Products warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). Hi-Performance Products **DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

NOTE: Hi-Performance Products does not assume any responsibility or liability for any, advice furnished, by it, or for the performance, or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and / or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.