

# HP183AS

## HP183AS

HP183AS is a satin weave lightly coated with an anti-static PTFE coating. The PTFE coating provides good release qualities while retaining the porosity required for off-gassing. The anti-static coating aids in the dissipation of static electricity.

### Typical Physical Properties

Property	Units	Value
Substrate		Fiberglass
Coating Material		PTFE
Widths Available	Inches	60
Weight	Oz./Yd. <sup>2</sup>	21.0
Thickness	Inches	0.024
Breaking Strength (Warp)	Lbs./In.	600
Breaking Strength (Fill)	Lbs./In.	450
Trapezoidal Tear (Warp)	Lbs.	60
Trapezoidal Tear (Fill)	Lbs.	40
Porosity	SCFM/Ft. <sup>2</sup>	>5
Elongation at 40 lbs./in.	%	1.0 Maximum

The data listed above is for reference only. It is not intended for use as a guarantee of product performance.

Hi-Performance Products, INC.  
1231 Puerta Del Sol, Unit 400  
San Clemente CA 92673  
Customer Service: (949)366-6088

[ptfeglass.com](http://ptfeglass.com)

Limited Warranty: For a period of 6 months from the date of first sale, Hi-Performance Products warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). Hi-Performance Products DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Hi-Performance Products does not assume any responsibility or liability for any, advice furnished, by it, or for the performance, or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and / or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.