

HPN2A

HPN2A

HPN2A is a heavyweight fabric for use in industrial applications. Its high strength and tear resistance make it a good product for use as a release sheet, chemical/heat barrier or in moderate size belting. It is not designed for use in belting applications that require low elongation characteristics.

Typical Physical Properties

Property	Units	Value
Substrate	—	Fiberglass
Coating Material	—	PTFE
Widths Available	Inches	150
Weight	Oz./Yd. ²	38.0
Thickness	Inches	0.028
Breaking Strength (Warp)	Lbs./In.	600
Breaking Strength (Fill)	Lbs./In.	400
Trapezoidal Tear (Warp)	Lbs.	50
Trapezoidal Tear (Fill)	Lbs.	60
Elongation at 40lbs./In.	%	up to 2.0
Porosity	SCFM/Ft. ²	Non-Porous

The data listed above is for reference only. It is not intended for use as a guarantee of product performance.

Hi-Performance Products, INC.
1231 Puerta Del Sol, Unit 400
San Clemente CA 92673
Customer Service: (949)366-6088

ptfeglass.com

Limited Warranty: For a period of 6 months from the date of first sale, Hi-Performance Products warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). Hi-Performance Products **DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

NOTE: Hi-Performance Products does not assume any responsibility or liability for any, advice furnished, by it, or for the performance, or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and / or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.