

KCF 17 HW

KCF 17 HW

KCF 17 HW is a belting product used in applications that require high strength and low elongation. This material has inherent stability that enhances its ability to resist ridging, puckering and creasing. The surface is textured because of the use of large yarns in the fiberglass substrate.

Typical Physical Properties

Property	Units	Value
Widths Available	Inches	58
Weight	Oz./Yd.2	20.0
Thickness	Inches	0.017
Breaking Strength (Warp)	Lbs./In.	450
Breaking Strength (Fill)	Lbs./In.	550
Trapezoidal Tear (Warp)	Lbs.	70
Trapezoidal Tear (Fill)	Lbs.	50
Porosity	SCFM/Ft.2	Non-Porous
Elongation at 40 lbs./in.	%	1.0 Maximum

The data listed above is for reference only. It is not intended for use as a guarantee of product performance.

Hi-Performance Products, INC.
1231 Puerta Del Sol, Unit 400
San Clemente CA 92673
Customer Service: (949)366-6088

ptfglass.com

Limited Warranty: For a period of 6 months from the date of first sale, Hi-Performance Products warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). Hi-Performance Products **DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

NOTE: Hi-Performance Products does not assume any responsibility or liability for any, advice furnished, by it, or for the performance, or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and / or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.